



MI	Code	Ean Code	Pcs
750	1PB750	8020089998076	12
2000	1PB002	8020089998069	6
5000	1PB005	8020089998052	4

Vantaggi

- **Traspirante**
- **Non ingiallisce**
- **Certificato per alimenti**
- **Migliora la manutenzione della superficie**
- **Nessun odore sgradevole**
- **Non altera aspetto naturale della pietra**

Advantages

- **Breathable**
- **Non yellowing**
- **Maintains natural effect**
- **Easy maintenance**
- **Safe on food handling surfaces**
- **Low odour**



IDROPOL

ANTI MACCHIA PIANI MARMO E GRANITO LUCIDI



TOP CUCINE - BAR BAGNI - TAVOLI DAVANZALI

Tattamento anti macchia specifico per marmi, graniti e pietre naturali lucidi e levigati utilizzato nel settore dell'arredamento quali: tavoli e top di bagni e cucine. Il prodotto penetra nella porosità e lascia la superficie protetta dalle varie sostanze macchianti quali: olio, caffè e acqua, etc.

Modo d'uso



Applicare su superfici perfettamente pulite (utilizzare il prodotto POWER CLEAN con una diluizione 1:30 per la pulizia preventiva). Stendere il prodotto in modo uniforme sulla superficie da trattare. Lasciare asciugare alcune ore. Asportare successivamente eventuali residui di prodotto con la lana d'acciaio. Su superfici molto assorbenti, consigliamo di effettuare una 2ª stesura di prodotto dopo 3-4 ore dalla prima stesura. Attendere 24 ore prima di utilizzare la superficie.

Resa

Il consumo indicativo varia da 10-25 m²/litro.

ANTI STAIN FOR POLISHED MARBLE AND GRANITE



KITCHEN, BAR AND VANITY WORKTOPS TABLES - WINDOW SILLS

Specific anti stain treatment for honed and polished marble, granite and natural stone surfaces used within home furnishing such as; tables, kitchen worktops, bar and vanity tops. The product penetrates deep inside the surface pores leaving the surface protected against various staining substances such as: oil, coffee and water, etc.

How to use



Apply to perfectly clean surfaces (use POWER CLEAN diluted in water using a ratio of 1:30 for surface pre clean; to remove existing coatings, waxes or previous applied treatments use SOLV or DEWAX as directed). Apply the product in a uniform way. Leave to dry for a few hours and proceed to remove excess dry product from treated surface using a steel wool pad. Note: on very absorbent materials apply a second coat after 3-4 hours from the first application. Allow 24 hours for complete drying before using the treated surface.

Coverage

Indicated coverage varies from 10-15 m²/litre.