



Description

BEARINGS LOCKER

Details

To lock bearings, bushings, sliding blocks, oil retainers, pins, grooves and other cylindrical parts requiring possible disassembly. It locks and seals threaded metallic parts with medium strength resistance to disassembly.

PHYSICAL-CHEMICAL AND TECHNICAL PROPERTIES

Properties	Description	Chemical resistance*	T°C	100h	500h	1000h
Base	Metacrylic resin	Water/glycol	85	90	85	80
Colour	Brown	Brake liquid	22	95	90	85
Viscosity	400/600 mPa.s	Motor oil	125	95	90	90
Density	1.06	Acetone	22	100	90	90
Flash point	>100°C	*DIN-54454 test				
Unscrewing torque	ISO -10964 25/35 N.m					
Residual unscrew. torque	ISO -10964 18/22 N.m					
Service temperature range	-50>+150°C					
Maximum Slack	0.15 mm					

Important notes:

Speed of polymerisation

This is influenced by the nature of the materials and the temperature at which the reaction occurs. The ideal temperature for polymerisation is between 20°C and 25°C. Lower temperatures slow down the reaction, whereas higher temperatures speed it up.

Recommendations for use

Clean the parts, apply over the entire surface involved. Tighten completely. Do not move the joints and wait for it to harden for the required time. For the best results, you are advised to work on a clean, dry surface. On passivated metal surfaces use together with the Activator P730.

N.B.: Not suitable for metal-plastic bonds, in oxygen circuits or to seal systems with strongly oxidizing alkaline or acid products.
Shelf-life: 12 months at a temperature between +5°C and +28°C.

Packaging available

50ml

The information in this technical sheet is based on the specifications and potential use known to us. However, this data does not imply any legal obligation or liability whatsoever.

REGISTERED OFFICE
Via Domenico Scarlatti, 26
20124 Milan



Commercial Offices and Plant
Corso Europa, 91 – 20020 Solaro (MI)
info@farmicol.com
Customer Service +39 02 84505409
www.faren.com