



## Description

**CYANOACRYLATE FOR RUBBERS & PLASTICS**

## Details

For porous, irregular and vertical surfaces. It has a longer workability time than the liquid version, so there is time to check the exact position of the pieces.

**PHYSICAL-CHEMICAL AND TECHNICAL PROPERTIES**

Properties	Description
Appearance	Transparent liquid
Specific weight	1.10 kg/l
Viscosity	Isotropic gel
Shear resistance	>10/15 N/mm <sup>2</sup>
Reaction speed	5-180"
Flash point	>81°C
Maximum Slack	ND
Temperature resistance	-50>+80°C

Surfaces	Gluing times
Steel/steel	10-20"
Balsa wood-balsa wood	<7"
Aluminium-aluminium	<30"
Rubber/rubber	<5"
Pvc/pvc	3-10"
Nitrile-nitrile	<5"
Oak-oak	90-180"
Polycarbonate-polycarbonate	10-40"

## Important notes:

**Chemical resistance**

Good resistance to oils and solvents, diesel oil, ethanol, propanol and freon. Not recommended in systems transporting oxygen. Do not use if chlorinated compounds or other highly oxidant chemical products are present.

## Recommendations for use

Correctly align the parts to be glued. Ensure the parts are clean and dry. Apply the product directly from the can. Spread a small quantity on one surface only and press the parts firmly together.

**N.B.:** The less you use, the faster the parts will glue together.  
Shelf-life: 12 months in a cool place (ideal temperature +5°C)

## Packaging available

10-20 g

The information in this technical sheet is based on the specifications and potential use known to us. However, this data does not imply any legal obligation or liability whatsoever.

REGISTERED OFFICE  
Via Domenico Scarlatti, 26  
20124 Milan



Commercial Offices and Plant  
Corso Europa, 91 – 20020 Solaro (MI)  
[info@farmicol.com](mailto:info@farmicol.com)  
Customer Service +39 02 84505409  
[www.faren.com](http://www.faren.com)